

IN THE CLAIMS:

Claim 1 (Withdrawn): An etchant, comprising:

hydrogen peroxide (H₂O₂); and

a mixed solution including a neutral salt.

Claim 2 (Withdrawn): The etchant according to claim 1, further comprising a hydrogen peroxide (H₂O₂) stabilizer.

Claim 3 (Withdrawn): The etchant according to claim 1, wherein the etchant etches a double-layered metal layer that includes a copper (Cu) layer, and a molybdenum (Mo) layer.

Claim 4 (Withdrawn): The etchant according to claim 1, wherein the etchant etches a double-layered metal layer that includes a copper (Cu) alloy layer, and a molybdenum (Mo) layer.

Claims 5 and 6 (canceled).

Claim 7 (Withdrawn): The etchant according to claim 1, wherein the neutral salt is selected from ~~a group including~~ the group consisting of potassium chloride (KCl), sodium chloride (NaCl), potassium hydrogen sulfate (KHSO₄), and potassium metaperiodate (KIO₄).

Claim 8 (Currently Amended): A method of forming an array substrate for use in a thin film transistor liquid crystal display (TFT-LCD) device, comprising:

- forming a first metal layer on a substrate;

- patterning the first metal layer to form a gate line and a gate electrode extended from the gate line;

- forming a gate insulation layer on the substrate to cover the patterned first metal layer;

- forming an active layer on the gate insulation layer and over the gate electrode;

- forming an ohmic contact layer on the active layer;

- forming a second metal layer on the gate insulation layer to cover the ohmic contact layer and the active layer;

- forming a third copper metal layer on the second metal layer;

simultaneously patterning the second metal layer and the third copper metal layer to form a double-layered data line, a double-layered source electrode and a double-layered drain electrode using an etchant that includes hydrogen peroxide (H_2O_2), a H_2O_2 stabilizer, and ~~at least one of an organic acid, an inorganic acid and a~~ neutral salt; and

forming a pixel electrode contacting the double-layered drain electrode.

Claim 9 (original): The method according to claim 8, wherein the first metal includes copper.

Claim 10 (original): The method according to claim 8, wherein the second metal includes molybdenum.

Claim 11 (canceled).

Claim 12 (Previously Presented): The method according to claim 8, wherein the third copper metal layer includes copper alloy.

Claim 13 (original) The method according to claim 8, wherein the double-layered data line, double-layered source electrode and double-layered drain electrode include a copper (Cu) layer and a molybdenum (Mo) layer.

Claim 14 (original): The method according to claim 8, wherein the double-layered data line, double-layered source electrode and double-layered drain electrode include a copper (Cu) alloy layer and a molybdenum (Mo) layer.

Claim 15 (Canceled).

Claim 16 (Canceled).

Claim 17 (Previously Presented): The method according to claim 8, wherein the neutral salt is selected from the group consisting of potassium chloride (KCl), sodium chloride (NaCl), potassium hydrogen sulfate (KHSO₄), and potassium metaperiodate (KIO₄).